



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C08L 67/02, C09K 3/16, C08L 69/00, 77/00, 81/02, 55/02, 23/06, 23/16, 71/12</b>		<b>A1</b>	(11) International Publication Number: <b>WO 99/33918</b>
			(43) International Publication Date: 8 July 1999 (08.07.99)
(21) International Application Number: PCT/US98/27428		(81) Designated States: CA, JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 23 December 1998 (23.12.98)			
(30) Priority Data: 9/366003 24 December 1997 (24.12.97) JP		<b>Published</b> <i>With international search report.</i> <i>With amended claims.</i>	
(71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).			
(72) Inventor; and			
(75) Inventor/Applicant (for US only): KOBAYASHI, Toshikazu [JP/JP]; 3759-7, Kawachi-machi, Kawachi-gun, Tochigi 329-1104 (JP).			
(74) Agent: PHAM, Hanh, T.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).			
(54) Title: ANTISTATIC POLYMER COMPOSITION AND MOLDINGS THEREOF			
(57) Abstract			
<p>To provide an antistatic polymer composition that can manifest a uniform antistatic effect permanently with little change in the surface resistance of moldings owing to humidity. Along with a polyether-system ion-conducting polymer, an ion source e.g. comprising a source of carboxyl groups and a source of at least one metal ion that can react with these carboxyl groups and a plasticizer of the ion-conducting polymer are compounded in one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, compounds of polyphenylene oxide and polystyrene, ABS, polyethylene, polypropylene and EPDM.</p>			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## ANTISTATIC POLYMER COMPOSITION AND MOLDINGS THEREOF

### Field of the Invention

The present invention relates to an antistatic polymer composition used to  
5 mold parts for which an antistatic effect is demanded, such as the transfer  
medium-separating guide parts of electrophotographic devices such as copiers and  
laser printers, which are placed at specific locations to guide the transfer medium,  
e.g., paper or polyester film, to which the electrostatic latent image is transferred,  
from the light-sensitive drum to the transfer zone and also to the fixing roller and  
10 to convey it from the device. More specifically, it relates to an antistatic polymer  
composition that can maintain its antistatic effect permanently due to the  
combination of an ion-conducting polymer, an ion source, and a plasticizer of the  
ion-conducting polymer, and also to moldings thereof.

### Background of the Invention

15 Polymers such as polyesters and polyamides are widely used in various  
fields such as packaging materials, electrical/electronic parts, and automotive  
parts. However, the moldings are likely to become charged electrostatically, so  
they cause static electricity problems. For example, the transfer medium-  
separating guide parts placed at specific locations in electrophotographic devices  
20 such as copiers and laser printers cause paper jams when the paper becomes  
difficult to separate because of static electricity.

In the past, a low-molecular-weight antistatic agent composed mainly of  
surfactant was incorporated into the polymer at the molding process or applied to  
the molding's surface in a finishing process in order to control the surface specific  
25 resistance of the molding to  $10^{13}$ - $10^8\Omega$ . However, the antistatic effect of  
surfactants is brought about by the equilibrium moisture adsorbed on the  
surfactant, so a sufficient antistatic effect was not manifested under low humidity.  
Also, the surfactant is removed by rubbing back and forth or washing, and the  
antistatic effect disappears.

30 Hence, polymers in which conductive materials such as conductive carbon  
fibers or metal fibers are incorporated as filler, polymers in which hydrophilic or

conductive monomers are incorporated by copolymerization to lower the electrical resistance of the polymer itself, and polymers rendered antistatic by alloying a hydrophilic polymer in the polymer have been developed. Also, various antistatic agents such as polyether systems, quaternary ammonium salt systems, sulfonic acid systems, and betaine systems have been introduced as permanent antistatic agents for addition to polymers (*Plastics Age*, Nov. 1993, published by Plastics Age Co.).

Specific examples of antistatic polyester compositions include an antistatic polymer composition obtained by compounding a thermoplastic resin with at least one polyoxyalkylene glycol or derivative thereof, a monomer unit comprising a vinyl-system unsaturated sulfonic acid or salt thereof, and a vinyl-system polymer to which an unsaturated aliphatic carboxylic acid alkyl ester with an alkyl group having 1-15 carbon atoms is bonded (Japanese Patent Application Kokai Publication Sho 60-202150); a polyester film with an antistatic effect obtained by compounding polyethylene terephthalate with a polyethylene glycol having a weight-average molecular weight of 4,000 to 50,000, an alkali metal salt of an alkylsulfonic acid, and an alkali metal salt of alkylbenzenesulfonic acid (Japanese Patent Application Publication Hei 2-232257); a polymer mixture containing polyester and a copolyetherester block copolymer with a polyether block derived from poly(propylene oxide) glycol having an ethylene oxide content of 15-35 wt% and a number-average molecular weight of 1,500 to 3,000 and capped with ethylene oxide (Japanese Patent Application Kokoku Publication Hei 7-110918); a composition with a permanent antistatic effect comprising polyetherester obtained by polycondensation of an aromatic dicarboxylic acid with 6-20 carbon atoms and/or ester thereof, poly(alkylene oxide) glycol having a number-average molecular weight of 200-50,000, and a glycol with 2-8 carbon atoms and a polycarbonate resin (Japanese Patent Application Kokai Publication Hei 8-245869); a thermoplastic resin composition obtained by compounding an aromatic polycarbonate resin, a block copolyamide resin, an impact modifier, phosphorus-containing compound with a spiro ring structure, and a metal deactivator (Japanese Patent Application Kokai Publication Hei 9-12854); and a permanent

antistatic resin composition comprising a polyetherester composed of a *para*-oriented aromatic dicarboxylic acid component with 4-20 carbon atoms, a specific aromatic diol component ring-substituted with a sulfonate salt group, a glycol component of 2-10 carbon atoms, and a poly(alkylene oxide) component with a number average molecular weight of 200-50,000 and having two ester-forming functional groups in its molecules, and a thermoplastic resin such as ABS (Japanese Patent Application Kokai Publication Hei 9-176497). However, the development of polymer compositions that can manifest a more uniform antistatic effect in the molding's surface is desired.

### Problems this invention is to solve

The problem addressed by this invention is to provide an antistatic polymer composition that makes it possible for moldings to manifest a uniform antistatic effect permanently with little change in surface resistance owing to humidity. More specifically, the problem addressed by this invention is to provide an antistatic polymer composition that is ideally used for polymer moldings where static electricity is a problem, such as the transfer medium-separating guide parts placed at specific locations in electrophotographic devices.

Another object is to provide a polymer composition giving further water-repellency with maintaining excellent antistatic effect by reducing changes in surface resistivity of molded article therefrom, which is useful in moldings requiring both antistatic effect and water-repellency.

## Summary of the Invention

As a result of studies to solve such problems, the present inventors discovered that an outstanding antistatic effect can be provided by compounding an ion-conducting polymer, an ion source or electrolyte, and a plasticizer of the ion-conducting polymer in the matrix polymer. That is, the antistatic polymer composition according to the first of these inventions is characterized in that it contains

(A) one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene;


(B) a polyether-system ion-conducting polymer;

(C) an ion source comprising (i) a source of at least one carboxyl group or sulfo group selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl group or sulfo group of (i), solid electrolytes or polymer electrolytes ; and

(D) a plasticizer of the aforementioned polyether-system ion-conducting polymer (B).

The antistatic polymer composition that is the second invention is characterized in that the above-indicated polyether-system ion-conducting polymer is polyetherester amide.

The third invention is the antistatic polymer composition of the aforementioned item (1) or (2) characterized in that the aforementioned plasticizer (D) is a plasticizer represented by formula (1):



(wherein m is an integer of 1-3, n is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>).

The fourth invention is the antistatic polymer composition of any one of the aforementioned item(1) to (3) characterized in that it contains 40.0-98.4 wt% of polymer (A), 1.0-35.0 wt% of polyether-system ion-conducting polymer (B), 0.1-15.0 wt% of ion source (C), and 0.5-10.0 wt% of plasticizer (D) with respect to the weight of the composition as a whole.

The fifth invention is the antistatic polymer composition characterized in comprising:

(A) one or more polymers selected from the group consisting of ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM (ethylene/propylene/diene) elastomer;

(B) a polyether-system ion-conducting polymer;

(C) an ion source comprising (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes; and

(D) a plasticizer of the aforementioned polyether-system ion-conducting polymer (B).

The sixth invention is the antistatic polymer composition of any one of the aforementioned item(1) to (5) characterized in further comprising a water-repellent comprising fluorinated compounds, silicone compounds or a mixture thereof.

Still another invention is moldings such as the transfer medium-separating guide parts for electrophotographic devices and any molded items requiring antistatic effect and water-repellency characterized in that they are molded from the above antistatic polymer composition.

#### Detailed Description of the Invention

The antistatic polymer composition of this invention has antistatic properties of at least a degree that can control the surface specific resistance of moldings to  $10^{13}$ - $10^8 \Omega$ .

Polymer (A) of this invention is one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene.

The polyester is polyethylene terephthalate obtained by polycondensation of ethylene glycol and terephthalic acid, polybutylene terephthalate obtained by polycondensation of butanediol and terephthalic acid, or a copolymer of ethylene terephthalate or polybutylene terephthalate that contains another comonomer component in a range that provides physical or chemical properties. As

comonomer components used in manufacturing the copolymer, ethylene glycol, 1,2-propylene glycol, pentanediol, hexanediol, 1,4-cyclohexanedimethanol, and the like can be mentioned as the glycol component and isophthalic acid and naphthalenedicarboxylic acid can be mentioned as the dicarboxylic acid component.

The intrinsic viscosity of the polyester is 0.3-1.3, preferably 0.5-1.0, more preferably 0.6-0.9.

The polyesters ideally used in this invention are polyethylene terephthalate, polybutylene terephthalate, and compounds of these.

In addition, the polyesters of this invention also include melt-processible polyesters or polyester amides that can form an anisotropic molten phase, generally called thermotropic liquid crystal polymers. The constituents of such polymers are aromatic hydroxycarboxylic acids, aromatic dicarboxylic acids, aliphatic dicarboxylic acids, aromatic diols, aliphatic diols, aromatic hydroxylamines, and aromatic diamines. The melt-processible polyesters or polyester amides that can form an anisotropic molten phase are obtained by polymerizing one of these constituents or by copolymerizing two or more of these constituents.

The following specific examples can be mentioned: aromatic polyesters obtained by polymerizing one or more aromatic hydroxycarboxylic acids; aromatic polyesters obtained by polymerizing an aromatic dicarboxylic acid, one or more aliphatic dicarboxylic acid, an aromatic diol, and one or more aliphatic diols; aromatic polyesters obtained by polymerizing an aromatic hydroxycarboxylic acid as the main component and one or more components selected from the group consisting of aromatic dicarboxylic acids, aliphatic dicarboxylic acids, aromatic diols, and aliphatic diols; aromatic polyester amides obtained by polymerizing an aromatic hydroxylamine, one or more aromatic diamines, and one or more aromatic hydroxycarboxylic acids; aromatic polyester amides obtained by polymerizing an aromatic hydroxylamine, one or more aromatic diamines, one or more aromatic hydroxycarboxylic acids, an aromatic dicarboxylic acid, and one or more aliphatic carboxylic acid; and aromatic

polyester amides obtained by polymerizing an aromatic hydroxylamine, one or more aromatic diamines, one or more aromatic hydroxycarboxylic acids, an aromatic dicarboxylic acid, one or more aliphatic carboxylic acids, an aromatic diol, and one or more aliphatic diols.

5 As examples of aromatic hydroxycarboxylic acids, 4-hydroxybenzoic acid, 3-hydroxybenzoic acid, 2-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, and 5-hydroxy-2-naphthoic acid, and hydroxybenzoic acids substituted with halogens, alkyls, and aryls can be mentioned.

As aromatic dicarboxylic acids, terephthalic acid, isophthalic acid, 3,3N-  
10 diphenyldicarboxylic acid, 4,4 N -diphenyldicarboxylic acid, 1,4-naphthalenedicarboxylic acid, 1,5-naphthalenedicarboxylic acid, 2,6-naphthalenedicarboxylic acid, and alkyl- and halogen-substituted aromatic dicarboxylic acids such as *tert*-butylterephthalic acid and chloroterephthalic acid can be mentioned.

15 As aliphatic dicarboxylic acids, cyclic aliphatic dicarboxylic acids such as *trans*-1,4-cyclohexanedicarboxylic acid, *cis*-1,4-cyclohexanedicarboxylic acid, and 1,3-cyclohexanedicarboxylic acid and substituted derivatives of these can be mentioned.

As aromatic diols, the following can be mentioned: hydroquinone,  
20 diphenol, 4,4 N -dihydroxydiphenyl ether, 3,4 N -dihydroxydiphenyl ether, bisphenol A, 3,4 N -dihydroxydiphenylmethane, 3,3 N -dihydroxydiphenylmethane, 4,4 N-dihydroxydiphenylsulfone, 3,4 N -dihydroxydiphenylsulfone, 4,4 N -dihydroxydiphenyl sulfide, 3,4 N -dihydroxydiphenyl sulfide, 2,6 N -naphthalenediol, 1,6 N -naphthalenediol, 4,4 N -  
25 dihydroxybenzophenone, 3,4 N -dihydroxybenzophenone, 3,3 N -dihydroxybenzophenone, 4,4 N -dihydroxydiphenyldimethylsilane, and alkyl- and halogen-substituted derivatives of these.

As examples of aliphatic diols, cyclic, linear, and branched aliphatic diols such as *trans*-1,4-hexanediol, *cis*-1,4-hexanediol, *trans*-1,3-cyclohexanediol, *cis*-  
30 1,2-cyclohexanediol, ethylene glycol, 1,4-butanediol, 1,6-hexanediol, 1,8-octanediol, *trans*-1,4-cyclohexanedimethanol, *cis*-1,4-cyclohexanedimethanol, and

*cis*-1,4-cyclohexanedimethanol and substituted derivatives of these can be mentioned.

As examples of aromatic hydroxylamines and aromatic diamines, 4-aminophenol, 3-aminophenol, *p*-phenylenediamine, and *m*-phenylenediamine, and substituted derivatives of these can be mentioned.

The liquid crystal polymers used in this invention generally have a number-average molecular weight of approximately 2,000-200,000, preferably 5,000-50,000, and more preferably 10,000-20,000.

The liquid crystal polymers ideally used in this invention are copolymers of 4-hydroxybenzoic acid and 6-hydroxy-2-naphthoic acid and copolymers of hydroquinone, diphenol, terephthalic acid, 2,6-naphthalenedicarboxylic acid, 4-hydroxybenzoic acid, and 6-hydroxy-2-naphthoic acid.

The polyamide that is another matrix polymer of this invention is obtained by polycondensation of a diamine component and a dicarboxylic acid component. As examples, polyamides obtained by polymerizing one or more diamines selected from the group consisting of aliphatic alkylenediamines, aromatic diamines, and alicyclic diamines and one or more dicarboxylic acid selected from the group consisting of aliphatic dicarboxylic acids, aromatic dicarboxylic acids, and aliphatic aminocarboxylic acids, and compounds of these can be mentioned.

The aliphatic alkylenediamine may be linear or branched. As specific examples, ethylenediamine, trimethylenediamine, tetramethylenediamine, pentamethylenediamine, hexamethylenediamine, 1,7-diaminoheptane, 1,8-diaminooctane, 1,9-diaminononane, 1,10-diaminodecane, 2-methylpentamethylenediamine, and 2-ethyltetramethylenediamine can be mentioned. These aliphatic alkylenediamines can be used alone, or two or more can be used combined.

The aromatic diamines may be used alone, or two or more may be used combined. As an example, *p*-phenylenediamine, *o*-phenylenediamine, *m*-phenylenediamine, *p*-xylenediamine, and *m*-xylenediamine can be mentioned.

As specific examples of alicyclic alkylenediamines, 1,3-diaminocyclohexane, 1,4-diaminocyclohexane, 1,3-bis(aminomethyl)cyclohexane,

bis(aminomethyl)cyclohexane, bis(4-aminocyclohexyl)methane, 4,4N -diamino-3,3N -dimethyldicyclohexylmethane, isophoronediamine, and piperazine can be mentioned. These can be used alone, or two or more can be used combined.

As aliphatic dicarboxylic acids, adipic acid, sebacic acid, azelaic acid, and  
5 dodecanedioic acid can be mentioned. These can be used alone, or two or more can be used combined.

As examples of aromatic dicarboxylic acids, terephthalic acid, isophthalic acid, phthalic acid, 2-methylterephthalic acid, and naphthalenedicarboxylic acid can be mentioned, and as an example of aromatic aminocarboxylic acids, *p*-  
10 aminobenzoic acid can be mentioned. These aromatic monomers can be used alone, or two or more can be used combined.

As specific examples of aminocarboxylic acids,  $\epsilon$ -aminocaproic acid and T-aminoundecanoic acid can be mentioned. These can be used alone, or two or more can be used combined.

15 Also, the number-average molecular weight of the polyamide is 2,000-50,000, preferably 5,000-40,000, and still more preferably 7,000-30,000.

The polyamides ideally used in this invention are nylon 66, nylon 6, copolymer of nylon 66 and nylon 6, and compounds of these.

Polycarbonates are obtained by the ester-exchange method, which reacts  
20 bisphenol A with diphenyl carbonate in a molten state, and by the solution polycondensation method, which reacts bisphenol A with phosgene in pyridine as solvent and acid-acceptor.

The number-average molecular weight of the polycarbonate is 6,000-100,000, preferably 10,000-80,000, and still more preferably 15,000-50,000.

25 Polyoxymethylene homopolymer is obtained by polymerization of formaldehyde, and copolymer is obtained by polymerization of trioxane with a cyclic ether or cyclic formal.

The number-average molecular weight of polyoxymethylene is 8,000-150,000, preferably 12,000-100,000, and still more preferably 20,000-80,000 for  
30 both homopolymer and copolymer.

Polyphenylene sulfide is obtained by reacting *p*-dichlorobenzene and

sodium sulfide in a polar solvent such as *N*-methylpyrrolidone at a high temperature of 200°C or above.

The weight-average molecular weight of polyphenylene sulfide is 5,000-90,000, preferably 8,000-70,000, and still more preferably 10,000-60,000.

5 With respect to compounds of polyphenylene oxide and polystyrene, polyphenylene oxide and polystyrene have the property of mutually dissolving completely in all ratios, so they may be mixed in any ratio.

The compound of polyphenylene oxide and polystyrene ideally used in this invention is a compound for which the weight ratio of polyphenylene oxide to  
10 polystyrene is 70:30 to 50:50.

Other suitable matrix polymers of the present invention may be, for example, ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM(ethylene/propylene/diene) elastomer.

15 Ion-conducting polymer (B) used in this invention is a polyether-system ion-conducting polymer. Polyethers have good compatibility with the matrix polymers, polyester and polyamide, so a uniform antistatic effect can be provided to the surface of moldings.

As specific examples, polyethylene oxide, polyetherester amide, polyetheramideimide, ethylene oxide-epihalohydrin copolymer, and  
20 methoxypolyethylene glycol (meth)acrylate copolymer can be mentioned. Polyethers of low degree of crystallization are preferred, and polyetherester amides are especially preferred.

The content of the polyether-system ion-conducting polymer is 1.0-35.0 wt%, preferably 3.0-20.0 wt%, and still more preferably 4.5-12.5 wt%, with  
25 respect to the weight of the composition. If less than 1.0 wt%, the antistatic effect will be insufficient, and if more than 35.0 wt%, this will lead to a decline in mechanical properties.

Ion source (C) used in this invention comprises

(i) a source of at least one carboxyl group or sulfo group selected from the  
30 group composed of hydrocarbon acids with 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group and

(ii) a source of at least one metal ion that is selected from the group composed of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes.

5 Solid electrolytes or polymer electrolytes are used instead of the ion source comprising the source of carboxyl group or sulfo group defined (i) and metal ion source defined (ii) in the antistatic polymer composition of this invention according to the intended application of use. Examples of the solid electrolytes include chemical composition which is expressed by XY or XW<sub>2</sub> wherein X is  
10 Li, Na, K, or NH<sub>4</sub>, Y is ClO<sub>4</sub>, I, BF<sub>4</sub>, or CF<sub>3</sub>SO<sub>3</sub> and W is Mg, Ca, Zn, or Cu.

In addition, polymer electrolytes capable of being used in this invention represent a wide range of compositions that can, for example, be polystyrenesulfonic acid sodium salt and acrylate copolymer ammonium salt.

By including the ion source, ions can be sufficiently supplied to the  
15 aforementioned ion-conducting polymer, so the ion-conducting polymer can sufficiently manifest an antistatic effect.

Preferably, carboxyl-group or sulfo group source (i) is a source of at least one carboxyl group or sulfo group [selected from the group] consisting of hydrocarbon acids containing 7 6-25 carbon atoms, sulfonic acids and organic  
20 polymers that contain pendant carboxyl groups or sulfo groups.


More preferably, ionomers composed of organic ionic hydrocarbon copolymers of  $\alpha$ -olefins with 2-5 carbon atoms and  $\alpha$ ,  $\beta$ -ethylenically unsaturated carboxylic acids with 3-5 carbon atoms whose carboxyl groups are at least partially neutralized with sodium or potassium cations are ideally used.

25 Other suitable ionomers contain (i) polyethylene terephthalate and/or polybutylene terephthalate oligomer and (ii) a substance derived from a sodium and/or potassium ion source that can react with the oligomer-like carboxyl end groups of (i).

The content of the ion source is 0.1-15.0 wt%, preferably 0.3-12.0 wt%,  
30 more preferably 1.0-8.0 wt%, with respect to the weight of the composition. If less than 0.1 wt%, the antistatic effect will be insufficient, and if more than 15.0 wt%,

this will lead to a decline in mechanical properties. The ion source contains a sufficient amount of the metal ion source that the concentration of metal in the composition will be greater than 1.0 wt%.

Plasticizer (D) used in this invention has a plasticizing effect on the polyether-system ion-conducting polymer used. As specific examples, phthalate ester plasticizers such as dimethyl phthalate, dibutyl phthalate, butyl benzyl phthalate, and di-2-ethylhexyl phthalate, phosphate ester plasticizers such as tricresyl phosphate and triphenyl phosphate, sulfonamide plasticizers such as *o,p*-toluenesulfonamide, *N*-ethyl-*o,p*-toluenesulfonamide, *N*-methylbenzenesulfonamide, *N*-ethylbenzenesulfonamide, and *N*-butylbenzenesulfonamide, and polyether system plasticizers can be mentioned. The preferred plasticizer is represented by formula (1):



wherein *m* is an integer of 1-3, *n* is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>.

Because the composition of this invention contains a plasticizer, the ions can easily move under high-temperature conditions, so the higher the temperature at which the molding is used, the more outstanding the antistatic effect that can be manifested.

The preferred plasticizer is obtained when *m* is 1, or *n* is 4-14, or X is H, and especially when *m* is 1, *n* is 4-14, and also X is H. The more preferred plasticizer is obtained when *m* is 1, or *n* is 7-13, or X is H, or A is an acyl with 8 carbon atoms or methyl, or B is an acyl with 8 carbon atoms, and especially when *m* is 1, *n* is 7-13, X is H, A is an acyl with 8 carbon atoms or methyl, and B is an acyl with 8 carbon atoms.

The preferred specific examples are polyethylene glycol 400 bis(2-ethylhexanoate), methoxypolyethylene glycol 550 2-ethylhexanoate, and tetraethylene glycol bis(2-ethylhexanoate). Of these, polyethylene glycol 400 bis(2-ethylhexanoate) is most ideally used.

The amount of plasticizer contained is 0.5-10.0 wt%, preferably 1.0-8.0 wt%, and still more preferably 2.0-6.0 wt% with respect to the weight of the composition. If less than 0.5 wt%, the antistatic effect will not be sufficient, and if more than 10.0 wt%, this will lead to a decline in mechanical properties.

5 Well-known flame retardants can be mixed in the composition of this invention. Specifically, brominated flame retardants such as polydibromostyrene, polytribromostyrene, polypentabromostyrene, decabromodiphenyl, tetrabromodiphenyl, hexabromodiphenyl ether, octabromodiphenyl ether, decabromodiphenyl ether, tetrabromodiphenyl sulfide, polypentabromobenzyl  
10 acrylate, brominated phenoxy resin, and epoxy-terminated phenoxy resin [sic] can be mentioned. Epoxy-terminated phenoxy resin [sic] and brominated polystyrene are preferred. The loading of flame retardant is usually 7-20 wt% based on the weight of the composition.

Along with the flame retardant, antimony compounds well known as  
15 flame-retarding assistants, such as antimony oxides and sodium antimonate, may be compounded.

Inorganic fillers commonly used to reinforce engineering plastics can also be compounded. As specific examples of inorganic fillers, glass fibers, carbon fibers, potassium titanate, whiskers, kaolin, clay, talc, wollastonite, calcium  
20 carbonate, silica, and mica can be mentioned. Glass fibers are ideally used. The loading of inorganic filler is usually 5-60 wt% based on the weight of the composition.

In addition to the above components, the composition of this invention may be compounded with commonly used additives such as impact modifiers,  
25 heat stabilizers, antioxidants, dyes, pigments, and release agents in ranges that do not impair its properties.

Also, it is possible to obtain a polymer giving significant improvements in both antistatic effect and water-repellency by adding any water-repellents, such as fluorinated compounds, silicone compounds or chemical compositions thereof that  
30 have low surface free energy and well known in the art, in appropriate amounts in addition to the aforementioned antistatic polymer composition of this invention.

When the water-repellent is used in combination with a low-molecular-weight antistatic agent composed mainly of surfactant incorporated into the polymer at the molding process or applied to the molding's surface in a finishing process, it may be able to improve sliding characteristics by reducing coefficient of kinetic friction, but can easily cause static electricity resulting into static electricity problem. Examples of the water-repellents are PTFE, PFA, FEP, ETFE, modified silicone such as silicone oil, silicone gum, amino-modified silicone and epoxy-modified silicone, fluorosilicone and perfluoroalkyl group containing oligomer.

The polymer composition of this invention can be manufactured by any well-known method used in the past. For example, it can be melt blended using the mixing devices generally used, such as the Banbury mixer, extruders, and various kneaders. With respect to the order of blending, all the components may be blended at the same time, or the ion-conducting polymer, ion source, and plasticizer may be fed from side feeders.

The composition of this invention can be used to manufacture moldings that are used in devices for which static electricity is a problem, such as the transfer medium-separating guide parts placed at specific locations in electrophotographic devices by a well-known method such as injection molding.

Also, it is possible to obtain products formed by molding the antistatic polymer composition of this invention, which has surface resistivity in the range of  $10^7$  to  $10^{13} \Omega$ , as measured according to test method of ASTM D 257 and is capable of being applied an electrostatic painting directly onto surface of the molded article without any primer. Since the molded articles made from the antistatic polymer composition of this invention don't require to be applied any surface treatment agent such as a solution in alcohol containing 0.5 to 1 % by weight of surfactant on the surface of the molded article to reduce its surface specific resistance by moisture absorption by the surfactant, the electrostatic painting may be used for the molded articles made from the antistatic polymer composition of this invention.

### Practical examples

This invention will now be explained with practical examples, but it is not

limited to only these examples.

Practical Example 1, Comparative Examples 1-5

The components shown in Table 1 were melt blended with a twin-screw extruder (ZSK-40 manufactured by W&P). After water cooling, pellets were  
5 manufactured. The pellets obtained were used to mold test pieces (7.5 mm x 12.5 mm x 3 mm). The mold temperature and resin temperature when molding were 110°C and 290°C, respectively.

The test pieces obtained were used to determine surface resistivity and volume resistivity. The results are shown in Table 1. The methods of  
10 determination were as follow:

Method for determining surface resistivity: Based on ASTM D257

Method for determining volume resistivity: Based on ASTM D257

The components referred to in the tables are as follows:

Polymer: Polyethylene terephthalate with an intrinsic viscosity of 0.65  
15 (trade name Rynite manufactured by DuPont).

Ion-conducting polymer: Polyetherester amide copolymer (trade name Perestat 6321 manufactured by Sanyo Chemical Industries)

Ion source: Sodium-neutralized ethylene-methacrylic acid copolymer with  
60% of the carboxylic acid of a copolymer composed of ethylene-methacrylic  
20 resin (weight ratio 85/15) neutralized with sodium (trade name Surlyn 8920 manufactured by DuPont)

Plasticizer: Polyethylene glycol 400 bis(2-ethylhexanoate) (trade name Rionon DEH-40 manufactured by Lion K.K.)

Glass fibers: PPG3540 chopped strand

Table 1

	PE 1*	CE 1*	CE 2	CE 3	CE 4	CE 5
polymer (wt%)	58.5	70.0	65.0	64.0	61.5	60.0
Ion-conducting polymer (wt%)	6.0	0	0	6.0	6.0	6.0
Ion source (wt%)	4.0	0	3.5	0	0	4.0
Plasticizer (wt%)	2.5	0	1.5	0	2.5	0
Glass fibers (wt%)	30.0	30.0	30.0	30.0	30.0	30.0
Surface resistivity $\Omega$	8.91 H $10^{12}$	1.94 H $10^{16}$	2.00 H $10^{17}$	2.24 H $10^{16}$	1.92 H $10^{14}$	5.40 H $10^{13}$
Volume resistivity ( $\Omega$ -cm)	1.45 H $10^{13}$	8.00 H $10^{15}$	1.30 H $10^{16}$	2.75 H $10^{15}$	2.95 H $10^{14}$	1.4 H $10^{14}$

\*PE = Practical Example CE = Comparative Example

When Practical Example 1 and Comparative Examples 1-5 were compared, the molding made from the composition of this invention had high surface specific resistance and volume specific resistance and was superior in antistatic effect.

When Comparative Example 3 and Comparative Example 4 were compared, it was found that the antistatic effect is improved by using a plasticizer along with the ion-conducting polymer, and when Comparative Example 3 and Comparative Example 5 were compared, it was found that the antistatic effect is also improved by using an ion source along with the ion-conducting polymer. However, neither case showed improvement in antistatic effect to the extent of Practical Example 1, in which both a plasticizer and an ion source were used along with the ion-conducting polymer.

#### Practical Examples 2-5, Comparative Examples 6-9

Test pieces were molded using a composition comprising 41.0 wt% of polyethylene terephthalate having an intrinsic viscosity of 0.65 (trade name Rynite manufactured by DuPont), 5.5 wt% of polyetherester amide copolymer (trade name Perestat 6321 manufactured by Sanyo Chemical Industry), 3.5 wt% of ethylene-methacrylic acid copolymer neutralized with sodium (trade name Surlyn 8920 manufactured by DuPont), 1.5 wt% of polyethylene glycol 400 bis(2-ethylhexanoate) (trade name Rionon DEH-40 manufactured by Lion K.K.), 13.0 wt% of polytribromostyrene (Pyro-chek 68 manufactured by Nissan Ferro), 0.5 wt% of antimony trioxide, and 35.0 wt% of glass fibers (PPG3540 chopped strand) for the

practical examples.

Test pieces were molded using a composition comprising 99.0 wt% of polyethylene terephthalate having an intrinsic viscosity of 0.65 (trade name Rynite manufactured by DuPont) and 1.0 wt% of sodium alkylsulfonate as the

comparative examples.

The test pieces obtained were used to test the effects of temperature and humidity on surface specific resistance. The results of measurement at 25°C, 50°C, 80°C, and 120°C are shown in Tables 2, 3, 4, and 5, respectively.

Table 2

Temperature: 25°C

Humidity (%)	Surface resistivity ( $\Sigma$ )	
	Practical Example 2	Comparative Example 6
10	$3.66 \text{ H } 10^{11}$	$1.19 \text{ H } 10^{16}$
30	$1.59 \text{ H } 10^{10}$	--
50	$1.17 \text{ H } 10^{10}$	$7.56 \text{ H } 10^{10}$
70	$2.77 \text{ H } 10^{10}$	--
95	$1.43 \text{ H } 10^{10}$	$1.35 \text{ H } 10^{10}$

Table 3

Temperature: 50°C

Humidity (%)	Surface resistivity ( $\Sigma$ )	
	Practical Example 3	Comparative Example 7
10	$7.75 \text{ H } 10^9$	$4.86 \text{ H } 10^{14}$
30	$3.58 \text{ H } 10^9$	--
50	$1.71 \text{ H } 10^9$	$3.65 \text{ H } 10^9$
70	$7.83 \text{ H } 10^8$	--
95	$5.81 \text{ H } 10^7$	$3.92 \text{ H } 10^8$

Table 4

Temperature: 80°C

Humidity (%)	Surface resistivity ( $\Sigma$ )	
	Practical Example 4	Comparative Example 8
10	$1.12 \text{ H } 10^9$	$2.97 \text{ H } 10^{14}$
30	$4.98 \text{ H } 10^8$	--
50	$5.40 \text{ H } 10^8$	$7.57 \text{ H } 10^{10}$
70	$1.44 \text{ H } 10^8$	--
95	$2.73 \text{ H } 10^7$	$1.30 \text{ H } 10^8$

Table 5

Temperature: 120°C

Humidity (%)	Surface resistivity ( $\Omega$ )	
	Practical Example 5	Comparative Example 9
10	$1.46 \text{ H } 10^9$	$5.67 \text{ H } 10^{12}$

5 Under any of the temperature conditions, the difference between the surface specific resistance of the practical examples and comparative examples became greater as the humidity became lower, and a difference arose in their antistatic effects. And even at the same humidity, the antistatic effect of the comparative examples declined as the temperature increased, but the antistatic  
10 effect of the practical examples increased as the temperature increased.

Practical Example 6 and Comparative Example 10

The same test pieces as in Practical Example 2 and Comparative Example 6, respectively, were used. To investigate durability of rubbing resistance, the surface was wiped with a cloth moistened with water or with a dry cloth, and  
15 surface specific resistivity was determined.

Table 6

Temperature: 25°C, humidity: 50%

Number of times wiped with damp cloth	Surface resistivity ( $\Omega$ )	
	Practical Example 6	Comparative Example 10
0	$1.17 \text{ H } 10^{10}$	$7.56 \text{ H } 10^{10}$
1	$1.99 \text{ H } 10^{10}$	$1.59 \text{ H } 10^{15}$
5	$2.00 \text{ H } 10^{10}$	$3.24 \text{ H } 10^{14}$
Number of times wiped with dry cloth		
5	$1.15 \text{ H } 10^{10}$	$5.67 \text{ H } 10^{14}$

Whether wiped with a damp cloth or dry cloth, there was no change in the  
20 antistatic effect of moldings made from the composition of this invention, but when a surfactant was used as in the comparative example, rubbing caused the antistatic effect to decline.

Examples 7 - 11 and comparative examples 11 and 12

In addition to the matrix polymer, ion-conducting polymer, plasticizer and

glass fibers used in Example 1 and Comparative examples 1 - 5 summarized in Table 1, and additional various ion sources in amount, all as specified in Table 7. The results of surface and volume resistivities measured according to ASTM D257 are also given in Table 7.

5

Table 7

	PE 7*	PA 8*	PA 9	PA 10	PA 11	CE 11	CE12
polymer (wt%)	62	62	59.5	62.4	51.5	62.45	62.42
Ion-conducting polymer (wt%)	6.0	6.0	6.0	6.0	13	6.0	6.0
Ion source A (wt%)					4		0.08
Ion source B (wt%)	0.5					0.05	
Ion source C (wt%)		0.5					
Ion source D (wt%)			3				
Ion source E (wt%)				0.1			
Plasticizer (wt%)	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Glass fibers (wt%)	30.0	30.0	30.0	30.0	30.0	30.0	30.0
Surface resistivity ( $\Omega$ )	$9.67 \times 10^{12}$	$1.26 \times 10^{13}$	$1.67 \times 10^{11}$	$8.62 \times 10^{11}$	$1.89 \times 10^9$	$5.51 \times 10^{14}$	$3.26 \times 10^{14}$
Volume resistivity ( $\Omega$ -cm)	$7.21 \times 10^{12}$	$8.26 \times 10^{12}$	$4.83 \times 10^{12}$	$2.28 \times 10^{11}$	$2.28 \times 10^8$	$1.89 \times 10^{14}$	$2.41 \times 10^{14}$

\*PE = Practical Example CE = Comparative Example

Ion source A: Sodium-neutralized ethylene-methacrylic acid copolymer with 60% of the carboxylic acid of a copolymer composed of ethylene-methacrylic resin (weight ratio 85/15) neutralized with sodium (trade name Surlyn 8920 manufactured by DuPont),

Ion source B: Sodium Montanate, commercially available under the tradename Hostamont NaV 101 from Clariant Japan, Inc.

Ion source C: Lithium Montanate, commercially available under the tradename Hostmont LiV 103 from Clariant Japan, Inc.

Ion source D: Polystyrenesulfonic acid sodium salt,

Ion source E: Lithium Iodide

#### Examples 11 - 13 and Comparative examples 13 - 18

To see the effect of adding water-repellents in addition to the antistatic polymer composition of this invention, additional formulations of examples 11 - 13 and comparative examples 13 - 18 were prepared, as summarized in the following Table 8. Using water-repellent of fluorinated compounds or silicone

20

compounds instead of the surfactant, Examples 11 -13, is seen to provide both water-repellency maintaining and antistatic effect.

The results, as to whether or not water-repellency is improved, and the values of water-repellent angle measured by the commonly known test method, are also given in Table 8.

Table 8

	PE 11	PA12*	PA13	CE13	CE14	CE 15	CE16	CE17	CE18
polymer (wt%)	54.5	42.5	56	66	54	67.5	57.5	69	70
Ion-conducting polymer (wt%)	6.0	6.0	6.0				6.0		
Ion source (wt%)	4	4	4		4		4		
Water-repellent A (wt%)	3			3					
Water-repellent B (wt%)		15			15				
Water-repellent C (wt%)			1.5			1.5			
surfactant (wt%)				1	1	1		1	
Plasticizer (wt%)	2.5	2.5	2.5				2.5		
Glass fibers (wt%)	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0
Surface resistivity ( $\Omega$ )	5.22x 10 <sup>12</sup>	6.95x 10 <sup>12</sup>	4.88x 10 <sup>12</sup>	8.62x 10 <sup>11</sup>	2.76x 10 <sup>12</sup>	5.51x 10 <sup>14</sup>	8.91x 10 <sup>12</sup>	4.88x 10 <sup>12</sup>	4.88x 10 <sup>16</sup>
Water repellent angle (°)	107	103	109	49	38	46	58	32	68

\*PE = Practical Example CE = Comparative Example

Water-repellent A: Silicone oil master batch, commercially available under the tradename BY27-009 from Toray Dow Silicone, Inc.

Water-repellent B: PTFE powder, commercially available under the tradename MP 1500 from DuPont,

Water-repellent C: Perfluoroalkyl acrylate-alkylacrylate block copolymer, commercially available under the tradename Megafac 178RM from DaiNippon Ink Co., Ltd.

Surfactant : Alkyl-benzene sulfonic acid sodium salt compound, commercially available under the tradename Chemistat 3033 from Sanyo Kasei Kogyo Inc.


Effects of the invention

According to this invention, it was possible to provide an antistatic polymer composition that is able to manifest a uniform antistatic effect permanently with little change in the surface resistance of moldings owing to humidity. The moldings molded from the polymer composition of this invention are ideally used in devices where static electricity is a problem.

### Claims

What is claimed is:

1. An antistatic polymer composition characterized in that it comprises:
  - (A) one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene;
  - (B) a polyether-system ion-conducting polymer;
  - (C) an ion source comprising: (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group; and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes; and
  - (D) a plasticizer of the aforementioned polyether-system ion-conducting polymer (B).
2. The antistatic polymer composition of Claim 1 characterized in that the polyether-system ion-conducting polymer (B) is a polyetherester amide.
3. The antistatic polymer composition of Claim 1 characterized in that plasticizer (D) of the polyester-system ion-conducting polymer (B) is a plasticizer represented by formula (1)



wherein m is an integer of 1-3, n is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>.

4. The antistatic polymer composition of Claim 1 characterized in that it contains 40.0-98.4 wt% of polymer (A), 1.0-35.0 wt% of polyether-system ion-conducting polymer (B), 0.1-15.0 wt% of ion source (C), and 0.5-10.0 wt% of

plasticizer (D) with respect to the weight of the composition as a whole.

5. Moldings characterized in that they are molded from the antistatic polymer composition of Claim 1.

6. Transfer medium-separating guide parts for electrophotographic devices characterized in that they are molded from the antistatic polymer composition of Claim 1.

7. A molded article made from the composition of claim 4 having surface resistivity in the range of  $10^7$  to  $10^{13}$  ohms, as measured under ASTM D 257 and being applied an electrostatic painting directly on surface thereof.

8. An antistatic polymer composition characterized in that it comprises

(A) one or more polymers selected from the group consisting of ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM(ethylene/propylene/diene) elastomer;

(B) a polyether-system ion-conducting polymer;

(C) an ion source comprising: (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group, and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl

groups or sulfo group of (i), solid electrolytes or polymer electrolytes; and

(D) a plasticizer of the aforementioned polyether-system ion-conducting polymer (B).


9. The composition of Claim 1 further comprising water-repellent comprising fluorinated compounds, silicone compound or a mixture thereof.

10. A molded article made from the composition of Claim 8.

## AMENDED CLAIMS

[received by the International Bureau on 15 June 1999 (15.06.99);  
original claims 1, 2, 3, 4 and 8 amended;  
remaining claims unchanged (3 pages)]

1. An antistatic polymer composition characterized in that it comprises:
  - (A) one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene;
  - (B) a ion-conductive polyether-based polymer;
  - (C) an ion source comprising: (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one carboxyl group or sulfo group; and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, ammonium ion, lithium ion, magnesium ion, calcium ion, copper ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes; and
  - (D) a plasticizer of the aforementioned ion-conductive polyether-based polymer (B).
2. The antistatic polymer composition of Claim 1 characterized in that the ion-conductive polyether-based polymer (B) is a polyetherester amide.
3. The antistatic polymer composition of Claim 1 characterized in that plasticizer (D) of the polyester-system ion-conducting polymer (B) is a plasticizer represented by formula (1)



wherein m is an integer of 1-3, n is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>.

4. The antistatic polymer composition of Claim 1 characterized in that it

contains 40.0-98.4 wt% of polymer (A), 1.0-35.0 wt% of ion-conductive polyether-based polymer (B), 0.1-15.0 wt% of ion source (C), and 0.5-10.0 wt% of plasticizer (D) with respect to the weight of the composition as a whole.

5. Moldings characterized in that they are molded from the antistatic polymer composition of Claim 1.

6. Transfer medium-separating guide parts for electrophotographic devices characterized in that they are molded from the antistatic polymer composition of Claim 1.

7. A molded article made from the composition of claim 4 having surface resistivity in the range of  $10^7$  to  $10^{13}$  ohms, as measured under ASTM D 257 and being applied an electrostatic painting directly on surface thereof.

8. An antistatic polymer composition characterized in that it comprises  
(A) one or more polymers selected from the group consisting of ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM(ethylene/propylene/diene) elastomer;  
(B) a polyether-system ion-conducting polymer;  
(C) an ion source comprising: (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one carboxyl group or sulfo group and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, ammonium ion, lithium ion, magnesium ion, calcium ion, copper ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes ; and  
(D) a plasticizer of the aforementioned ion-conductive polyether-based polymer (B).

9. The composition of Claim 1 further comprising water-repellent

comprising fluorinated compounds, silicon compound or a mixture thereof .

10. A molded article made from the composition of Claim 8.

# INTERNATIONAL SEARCH REPORT

I. National Application No

PCT/US 98/27428

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L67/02 C09K3/16 C08L69/00 C08L77/00 C08L81/02  
C08L55/02 C08L23/06 C08L23/16 C08L71/12

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 839 245 A (SCHLOSSMAN I ET AL) 1 October 1974 see column 12, line 43-44; claims 1,8 ---	1-7,9
A	EP 0 303 489 A (TORAY INDUSTRIES) 15 February 1989 see page 6, line 15-16 ---	1
A	PATENT ABSTRACTS OF JAPAN vol. 013, no. 461 (C-645), 18 October 1989 & JP 01 178554 A (KANEKAFUCHI CHEM IND CO LTD), 14 July 1989 see abstract ---	8,10
A	US 4 548 978 A (GARRISON JR WILLIAM E) 22 October 1985 see claims 1,11-13 --- -/--	1,3,8

☒ Further documents are listed in the continuation of box C

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

19 April 1999

Date of mailing of the international search report

27/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Voigtländer, R

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 98/27428

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 242 158 A (TORAY INDUSTRIES) 21 October 1987 see page 17, line 8; claim 1 ---	1,2
A	EP 0 149 091 A (MOBAY CHEMICAL CORP) 24 July 1985 see claim 1 ---	1
A	US 3 636 135 A (GARFORTH JOHN DAVID) 18 January 1972 see claim 1 ---	1
A	US 4 218 549 A (BURZIN KLAUS ET AL) 19 August 1980 see claim 1; example 4 ---	1
A	EP 0 613 919 A (SANYO CHEMICAL IND LTD) 7 September 1994 -----	1,8

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/27428

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3839245 A	01-10-1974	AT 371493 B	27-06-1983
		AT 281273 A	15-11-1982
		BE 797627 A	01-10-1973
		CH 596251 A	15-03-1978
		DE 2315753 A	11-10-1973
		FR 2178205 A	09-11-1973
		GB 1432011 A	14-04-1976
		JP 49008472 A	25-01-1974
		LU 67332 A	03-10-1973
		NL 7304433 A, B,	02-10-1973
		ZA 7302089 A	27-11-1974
EP 0303489 A	15-02-1989	CA 1302623 A	02-06-1992
		DE 3853180 D	06-04-1995
		DE 3853180 T	17-08-1995
		ES 2070853 T	16-06-1995
		JP 1144417 A	06-06-1989
		JP 1873817 C	26-09-1994
		KR 9704933 B	10-04-1997
		KR 9709429 B	13-06-1997
		US 5096995 A	17-03-1992
US 4548978 A	22-10-1985	CA 1228186 A	13-10-1987
		EP 0173718 A	12-03-1986
		JP 6060277 B	10-08-1994
		JP 61501269 T	26-06-1986
		WO 8503717 A	29-08-1985
EP 0242158 A	21-10-1987	JP 1814672 C	18-01-1994
		JP 4028025 B	13-05-1992
		JP 62241945 A	22-10-1987
		JP 62265348 A	18-11-1987
		JP 7045612 B	17-05-1995
		JP 62273252 A	27-11-1987
		DE 3788818 D	03-03-1994
		DE 3788818 T	30-06-1994
		US 5500478 A	19-03-1996
		US 5834561 A	10-11-1998
		US 5886097 A	23-03-1999
		US 5338795 A	16-08-1994
EP 0149091 A	24-07-1985	JP 60141757 A	26-07-1985
US 3636135 A	18-01-1972	BE 738308 A	02-03-1970
		CH 520733 A	31-03-1972
		DE 1945111 A	12-03-1970
		FR 2019408 A	03-07-1970
		GB 1270097 A	12-04-1972
		JP 48025410 B	28-07-1973
		NL 6913556 A	09-03-1970
US 4218549 A	19-08-1980	DE 2716004 A	26-10-1978
		AU 516040 B	14-05-1981
		AU 3488778 A	11-10-1979
		BE 865815 A	09-10-1978
		BR 7802173 A	19-12-1978
		CA 1088244 A	21-10-1980
		CH 634087 A	14-01-1983

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/27428

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4218549 A		FR 2386582 A	03-11-1978
		GB 1602692 A	11-11-1981
		JP 1265242 C	27-05-1985
		JP 53126057 A	02-11-1978
		JP 57022349 B	12-05-1982
		NL 7803743 A, B,	11-10-1978
EP 0613919 A	07-09-1994	JP 2538512 B	25-09-1996
		JP 6313078 A	08-11-1994
		JP 2711988 B	10-02-1998
		JP 6313079 A	08-11-1994
		DE 69406476 D	04-12-1997
		DE 69406476 T	19-03-1994
		US 5652326 A	29-07-1997
		US 5604284 A	18-02-1997
		US 5886098 A	23-03-1999
		JP 6345927 A	20-12-1994
		JP 2565846 B	18-12-1996
		JP 7010989 A	13-01-1995
		JP 2631965 B	16-07-1997
		JP 7188475 A	25-07-1995